



## RTV110 Series

### One-Component Acetoxy Self Leveling Adhesive Sealants

#### Product Description

RTV112 and RTV118 one-component, ready-to-use adhesive sealants are extremely versatile. They cure to a tough, durable, resilient silicone rubber on exposure to atmospheric moisture at room temperature. Acetic acid vapors are released from the sealant surface as a by-product of cure.

RTV112 and RTV118 sealants are self-leveling products which are preferable to paste-consistency sealants when flow into small crevices and hard-to-reach places is desired.

Since all these sealants utilize a moisture cure system, they must not be used in thicknesses of greater than 6mm (1/4 in.).

Where section depths exceed 6mm (1/4 in.), GE Silicones one component, addition cure or two-component silicone rubber compounds are recommended.

#### Key Performance Properties

- One-component products
- Capability to cure at room temperature and ambient humidity
- Self adhesion properties
- Low temperature flexibility
- High temperature performance
- Excellent weatherability and ozone and chemical resistance
- Excellent electrical insulation properties

#### Applications

| Product                            | Features        | Potential Applications                                                                                                                  | UL         | Food Contact                                              |
|------------------------------------|-----------------|-----------------------------------------------------------------------------------------------------------------------------------------|------------|-----------------------------------------------------------|
| RTV112 White<br>RTV118 Translucent | General purpose | Electrical insulation, thin section potting, self leveling protective coatings. Will flow into small crevices and hard to reach places. | File 36952 | FDA 21 CFR 177.2600<br>USDA NSF International Std. No. 51 |

These sealants were not designed for and should not be used for applications intended for permanent implantation into the human body.

These sealants are not for use in delicate electrical and electronic applications in which corrosion of copper, brass or other sensitive metals is undesirable.

**Typical Product Data**

| <b>Uncured Properties</b>                                               | <b>RTV112, RTV118</b>              |
|-------------------------------------------------------------------------|------------------------------------|
| Consistency                                                             | Self leveling                      |
| Color                                                                   | RTV112 White<br>RTV118 Translucent |
| Viscosity, poises                                                       | 200                                |
| Application Rate, (g/min)                                               | —                                  |
| Specific Gravity                                                        | 1.05                               |
| Tack-Free Time, min.                                                    | 20                                 |
| <b>Cured Properties<sup>(1)</sup></b>                                   | <b>RTV112, RTV118</b>              |
| <b>Mechanical:</b>                                                      |                                    |
| Tensile Strength, kg/cm <sup>2</sup> (lb/in <sup>2</sup> )              | 23 (325)                           |
| Elongation, %                                                           | 325                                |
| Hardness, Shore A                                                       | 25                                 |
| Tear Strength, kg/cm (lb/in)                                            | —                                  |
| Shear Strength, kg/cm <sup>2</sup> (lb/in <sup>2</sup> ) <sup>(2)</sup> | 7 (100)                            |
| Peel Strength, kg/cm (lb/in) <sup>(3)</sup>                             | 3 (15)                             |

**Typical Product Data**

| <b>Electrical:</b>                                     | <b>RTV112, RTV118</b>  |
|--------------------------------------------------------|------------------------|
| Dielectric Strength, kv/mm (v/mil)                     | 16 (400)               |
| Dielectric Constant<br>@ 60 Hz                         | 2.8                    |
| Dissipation Factor<br>@ 60 Hz                          | .001                   |
| Volume Resistivity, ohm-cm                             | 6x10 <sup>14</sup>     |
| <b>Thermal:<sup>(4)</sup></b>                          |                        |
| Brittle Point, °C (°F)                                 | -60 (-75)              |
| Maximum continuous operating temperature, °C (°F)      | 204 (400)              |
| Maximum intermittent operating temperature,<br>°C (°F) | 260 (500)              |
| <b>Additional Information:<sup>(4)</sup></b>           |                        |
| Linear Shrinkage, %                                    | 1.0                    |
| Thermal Conductivity, cal/sec/cm <sup>2</sup> , °C/cm  | .0005                  |
| (Btu/hr/ft <sup>2</sup> , °F/ft)                       | (.12)                  |
| Coefficient of Expansion cm/cm, °C                     | 27x10 <sup>-5</sup>    |
| (in/in, °F)                                            | (15x10 <sup>-5</sup> ) |

(1) Cure time 3 days/25C (77F)/50% relative humidity.

(2) At 100% cohesive failure.

(3) At 100% cohesive failure using 1 in. x 8 in. stainless steel screen at 180° pull angle.

(4) Information is provided for customer convenience only. These properties are not tested on a routine basis.

**Specifications**

Typical product data values should not be used as specifications. Assistance and specifications are available by contacting GE Silicones at 800/255-8886.

**FDA STATUS**

RTV112 and RTV118 sealants can be used in food contact applications where [FDA](#) regulations apply. Reference CDS4319 “Food Contact Applications, Silicone Rubber Compounds”, for specific regulations, limitations and conditions of use.

**USDA STATUS**

RTV112 and RTV118 sealants may be used on equipment which may contact edible products in official establishments operating under the Federal meat and poultry products inspection program. See USDA letter of Authorization. Refer to GE Silicones bulletin CDS #4319 before use.

**NSF INTERNATIONAL STATUS**

NSF International lists RTV112 and RTV118 sealants under NSF International Standard No. 51 (Plastic Materials and Components for Use in Food Equipment), as satisfactory for use on food contact surfaces. Refer to GE bulletin CDS #4319 before use.

**UL STATUS**

RTV112 and RTV118 silicone rubber adhesive sealants are recognized by Underwriters Laboratories, Inc., under their Component Recognition Program ([UL](#) File No. E-36952). Refer to CDS4320 for additional information.

**MILITARY SPECIFICATION**

MIL-A-46106

|         |         |                                            |
|---------|---------|--------------------------------------------|
| Group I | Type II | General Purpose Flowable<br>RTV112, RTV118 |
|---------|---------|--------------------------------------------|

Testing for referenced MIL Spec is performed in accordance with current GE Silicones quality test methods, laboratory conditions, and procedures, frequency and sampling, which are not necessarily identical with the methods, conditions, procedures, frequency and sampling stated or referenced in the listed specification. Any certification will be limited to listed properties and will not imply or state conformity to any other aspect of the referenced specification, including but not limited to marking, packaging, bar coding, testing, or sampling. Contact GE Silicones for a comparison review.

**Surface Preparation**

RTV112 and RTV118 sealants will bond to many clean surfaces without the aid of primers. These surfaces typically include many metals, glass, ceramic, silicone rubber and some rigid plastics. These adhesive sealant products will also produce fair bonds to organic rubber and to some flexible plastics not containing fugitive plasticizers (which migrate to the surface, impairing adhesion). An evaluation should be made to determine bond strength for each specific application. For difficult-to-bond substrates, use of a primer is suggested. Primers SS4004, SS4044 and SS4179 are recommended for use with these sealants. Complete information and usage instructions for these primer products are contained in a separate product data sheet, (CDS #1532).

Where adhesion is required, surfaces should be thoroughly cleaned with a suitable solvent such as naphtha or methyl ethyl ketone (MEK) to remove dirt, oil and grease. The surface should be wiped dry before applying the adhesive sealant.

When solvents are used, proper safety precautions must be observed.

**Application and Cure Time Cycle**

Paste-consistency products may be applied directly to clean or primed substrates. Where broad surfaces are to be mated, the sealant should be applied in a thin, less than 6mm (1/4 in.) diameter, bead or ribbon around the edge of the surface to be bonded.

Flowable products may be applied to clean or primed substrates by pouring directly from the original container or dipping. These products will self-level on a surface, filling small crevices and surface voids. Depth of potted sections should not exceed 6mm (1/4 in.).

The cure process begins with the formation of a skin on the exposed surface of the sealant and progresses inward through the material. At 25C (77F) and 50% relative humidity, RTV112 and RTV118 sealants will form a surface skin which is tack-free to the touch in 15 to 30 minutes. Once the tack-free skin has begun to form, further tooling of the adhesive sealant is not advisable.

Higher temperatures and humidity will accelerate the cure process low temperatures and low humidity will slow the cure rate.

As the adhesive sealant cures, acetic acid vapors are released from the sealant surface. The odor of acetic acid will completely disappear when curing is completed.

A 3mm (1/8 in.) section of adhesive sealant will cure through in approximately 24 hours at 25C (77F) and 50% R.H. Since cure time increases with thickness, use of these adhesive sealants should be limited to section thicknesses of 6mm (1/4 in.) or less.

## **Bond Strength Development**

In addition to the effects of temperature and relative humidity, development of maximum bond strength will depend on joint configuration, degree of confinement, sealant thickness and substrate porosity. Normally, sufficient bond strength will develop in 12 to 24 hours to permit handling of parts. Minimum stress should be applied to the bonded joint until full adhesive strength is developed. Eventually the adhesive strength of the bond will exceed the cohesive strength of the silicone rubber sealant itself. Always allow maximum cure time available for best results.

## **PACKAGING AND DISPENSING**

RTV adhesive sealants from GE Silicones are supplied ready-to-use in collapsible aluminum squeeze tubes, caulking cartridges and in bulk containers.

Collapsible aluminum tubes may be squeezed by hand or with the aid of mechanical wringers which allow more complete removal of material from the tube. Air-operated dispensing guns may also be used with aluminum tubes and offer the advantages of improved control and faster application for production line use. The sealant may be dispensed from caulking cartridges by using simple mechanical caulking guns or air-operated guns. Air-operated guns will allow greater control and application speed. Both tubes and cartridges are easy to use, can be put into production quickly and require minimal capital investment.

**Note:** Do not exceed 45 psig when used in air-powered caulking guns.

Bulk containers require a larger initial investment in dispensing equipment, but offer the most economical packaging for volume production. Bulk dispensing systems are air-operated extrusion pumps coupled to hand or automated dispensing units. Pumps which are specifically designed for pumping one-component RTV silicone rubber have TEFLON® seals, packing and lined hoses to prevent moisture permeation and pump cure problems. Specific details on dispensing systems and manufacturers are available in a separate GE Silicones RTV Silicone Rubber Equipment Guide (CDS #1541).

## **CLEAN UP AND REMOVAL**

Before curing, solvent systems such as naphtha or methyl ethyl ketone (MEK) are most effective. Refer to solvent use warnings in the section on surface preparation.

After cure, selected chemical strippers which will remove the silicone rubber are available from other manufacturers. Specific product information may be obtained on request.

### **Handling and Safety**

These products are manufactured and sold for industrial use only. Material Safety Data Sheets are available upon request from GE Silicones. Similar information for solvents and other chemicals used with our products should be obtained from your suppliers.

**Storage and Warranty  
Period**

The warranty period for RTV112 and RTV118 is 12 months from date of shipment from GE Silicones if stored in the original unopened containers in a dry location at temperatures less than 27C (80F).

**Availability**

GE Silicones rubber sealants may be ordered from GE Silicones, Waterford, NY 12188, the GE Silicones Sales office nearest you or an authorized GE silicone product distributor.

**Government  
Requirement**

Prior to considering use of a GE Silicones' product in fulfilling any Government requirement, please contact the Government and Trade Compliance office at 413-448-4624.

CDS4312

LEGAL

DISCLAIMER

THE MATERIALS, PRODUCTS AND SERVICES OF GE SILICONES, GE BAYER SILICONES, GE TOSHIBA SILICONES, THEIR SUBSIDIARIES OR AFFILIATES (THE "SUPPLIER"), ARE SOLD SUBJECT TO THE SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN APPLICABLE SALES AGREEMENTS, PRINTED ON THE BACK OF ACKNOWLEDGMENTS AND INVOICES, OR AVAILABLE UPON REQUEST. ALTHOUGH THE INFORMATION, RECOMMENDATIONS OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (I) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (II) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SUPPLIER'S MATERIALS, PRODUCTS, SERVICES, RECOMMENDATIONS OR ADVICE. NOTHING IN THIS OR ANY OTHER DOCUMENT SHALL ALTER, VARY, SUPERSEDE OR OPERATE AS A WAIVER OF ANY OF THE SUPPLIER'S STANDARD CONDITIONS OF SALE.

Each user bears the full responsibility for making its own determination as to the suitability of Supplier's materials, products, services, recommendations or advice for its own particular purpose. Each user must identify and perform tests and analyses sufficient to assure it that its finished parts will be safe and suitable for use under end-use conditions. Because actual use of products by the user is beyond the control of Supplier, such use is within the exclusive responsibility of the user, and Supplier cannot be held responsible for any loss incurred through incorrect or faulty use of the products. Further, no statement contained herein concerning a possible or suggested use of any material, product, service or design is intended or should be construed to grant any license under any patent or other intellectual property right of Supplier or any of its subsidiaries or affiliated companies, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.