



RTV162

Electronic Grade Silicone Adhesive Sealant

Product Description

RTV162 adhesive sealant from GE Silicones is one-component, ready-to-use electronic grade silicone sealant. It cures to a tough, resilient silicone rubber on exposure to atmospheric moisture at room temperature. The electronic-grade silicone adhesive sealant differ somewhat in physical properties including consistency.

RTV162 - white paste

Key Performance Properties

- Non-corrosive to electronic metals, including copper and brass
- Low odor cure, releasing an alcohol vapor from the sealant surface during cure
- [UL](#) Recognition. RTV162 is recognized by Underwriters Laboratories, Inc. under their Component Recognition Program (UL File No. E-36952). Refer to GE Silicone Publication (4320) for additional information.
- Retains elastomeric properties for long periods at temperatures from -60C (-75F) to 205C (400F) and for short periods up to 260C (500F).
- One component
- Cure at room temperature
- Excellent electrical insulation properties
- Excellent resistance to moisture, dust, dirt, UV, ozone and chemicals

Typical Product Data

Typical Uncured Properties	RTV162
Color	White
Consistency	spread able paste
Viscosity, poise	–
Specific Gravity	1.09
Application Rate, gm/min.	350
Tack-Free Time, hours	4
Cured Properties⁽¹⁾	
Mechanical	
Hardness, Shore A	35
Tensile Strength, kg/cm ² (lb/in ²)	38.2 (550)
Elongation, %	400
Peel Strength, kg/cm (lb/in) ⁽²⁾	7.2 (40)
Electrical⁽³⁾	
Dielectric Strength, kv/mm (v/mil)	18 (450)
Dielectric Constant @ 60 Hz	2.8
Dissipation Factor @ 60 Hz	.001
Volume Resistivity, ohm-cm	3x10 ¹⁵
Thermal⁽³⁾	
Brittle Point, °C (°F)	-60 (-75)
Maximum continuous operating temperature, °C (°F)	204 (400)
Maximum intermittent operating temperature, °C (°F)	260 (500)
Additional Information⁽³⁾	
Thermal Conductivity, cal/sec/cm ² , °C/cm	.0005
(Btu/hr/ft ² , °F/f)	(.12)
Coefficient of Expansion	27x10 ⁻⁵
cm/cm, °C (in/in, °F)	(15x10 ⁻⁵)

(1) Cure time 7 days at 25C (77F), 50% relative humidity.

(2) 1 in. x 8 in. stainless steel screen at 180° pull angle.

(3) Information is provided for customer convenience only. Properties are not tested on a routine basis.

Specifications

Typical product data values should not be used as specifications. Assistance and specifications are available by contacting GE Silicones at 800/255-8886

MILITARY SPECIFICATIONS

RTV162 sealant meets the physical requirements of MIL-A-46146. Testing is performed in accordance with current GE Silicones quality test methods, laboratory conditions, and procedures, frequency and sampling, which are not necessarily identical with the methods, conditions, procedures, frequency and sampling stated or referenced in MIL-A-46146. Any certification will be limited to listed properties and will not imply or state conformity to any other aspect of MIL-A-46146, including but not limited to marking, packaging, bar coding, testing, or sampling. Contact GE Silicones for a comparison review.

Instructions for Use

Applications

RTV162 is recommended for use in aerospace, automotive, appliance and other industries which incorporate electronic components into a finished product. Electronic and integrated circuits, semiconductors and copper connections are typical applications.

RTV162 adhesive sealant is recommended for sealing and bonding of electronic components onto printed circuit boards and protecting copper connections on electronic parts assemblies.

Surface Preparation

RTV162 adhesive sealant will bond to many clean surfaces without the aid of primers. These surfaces normally include many metals, glass, ceramic, silicone rubber and some rigid plastics. These adhesive sealants will also bond to some organic rubbers and flexible plastics not containing fugitive plasticizers (those that migrate to the surface impairing adhesion). An evaluation should be made to determine bond strength for each specific application.

For difficult-to-bond substrates, use of a primer is suggested. SS4004, SS4044 and SS4179 primers are recommended for use with RTV162 sealant. Complete information and usage instructions for these primer products are contained in a separate product data sheet, (CDS#1532).

Where adhesion is required, surfaces should be thoroughly cleaned with a suitable solvent to remove dirt, oil and grease. The surface should be dry before applying the adhesive sealant.

When solvents are used, proper safety precautions must be observed.

Cure Time Cycle

RTV162 adhesive sealant may be applied directly to a clean or primed substrate. The adhesive sealant begins to cure on exposure to moisture in the air at room temperature. Where broad surfaces are to be bonded the sealant should be applied in a thin, less than 6mm (¼ in.) diameter bead or ribbon around the edge of one of the surfaces.

The cure process begins with the formation of a skin on the exposed surface of the sealant and progresses inward through the material. At 25C (77F) and 50% relative humidity, these products will form a surface skin which is tack-free to the touch in about 4 hours. Once the tack-free skin has begun to form, further tooling of the adhesive sealant is not advisable.

High temperatures and high humidity will accelerate the cure process low temperatures and low humidity will slow the cure rate.

As the adhesive sealant cures, alcohol vapors are released from the sealant surface. This by-product of cure has a slight, but non-objectionable odor which will completely disappear after curing is completed.

A 3mm (1/8 in.) section of adhesive sealant will cure through in approximately 48 hours at 25C (77F) and 50% relative humidity. Since cure time increases with thickness, use of RTV162 sealant should be limited to section thicknesses of 6mm (¼ in.) or less.

PACKAGING AND DISPENSING

RTV162 adhesive sealant is supplied in caulking cartridges and bulk containers. RTV162 is also available in collapsible squeeze tubes.

Tubes may be squeezed by hand or with the aid of mechanical wringers which allow more complete removal of material from the tube. The sealant may be dispensed from caulking cartridges by using simple mechanical caulking guns or air-operated guns. Air-operated guns will allow greater control and application speed. Both tubes and cartridges are easy to use, can be put into production quickly and require minimum capital investment.

Note: Do not exceed 45 psig when used in air-powered caulking guns. Bulk containers offer the most economical packaging for volume production.

Bulk dispensing systems are air-operated extrusion pumps coupled to hand or automated dispensing units. Specific details on dispensing systems and manufacturers are available in a separate GE RTV Silicone Sealant Equipment Guide, (CDS1541).

Recommendations for pump selection and assistance in converting lines from other silicone systems to the RTV162 alkoxy cure system sealants are available from GE Silicones.

CLEAN UP AND REMOVAL

Before cure, solvent systems such as naphtha or methyl ethyl ketone (MEK) are effective.

Handling and Safety

Material Safety Data Sheets are available upon request from GE Silicones. Similar information for solvents and other chemicals used with our products should be obtained from your suppliers.

Storage and Warranty Period

The warranty period is 6 months from date of shipment from GE Silicones if stored in the original unopened container at or below 50°F.

Availability

Products may be ordered from GE Silicones, Waterford, NY 12188, the GE Silicones Sales office nearest you, or where appropriate an authorized GE silicone product distributor.

Government Requirement

Prior to considering use of a GE Silicones product in fulfilling any Government requirement, please contact the Government and Trade Compliance office at 413-448-4624.

CDS4500

LEGAL

DISCLAIMER

THE MATERIALS, PRODUCTS AND SERVICES OF GE SILICONES, GE BAYER SILICONES, GE TOSHIBA SILICONES, THEIR SUBSIDIARIES OR AFFILIATES (THE "SUPPLIER"), ARE SOLD SUBJECT TO THE SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN APPLICABLE SALES AGREEMENTS, PRINTED ON THE BACK OF ACKNOWLEDGMENTS AND INVOICES, OR AVAILABLE UPON REQUEST. ALTHOUGH THE INFORMATION, RECOMMENDATIONS OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (I) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (II) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SUPPLIER'S MATERIALS, PRODUCTS, SERVICES, RECOMMENDATIONS OR ADVICE. NOTHING IN THIS OR ANY OTHER DOCUMENT SHALL ALTER, VARY, SUPERSEDE OR OPERATE AS A WAIVER OF ANY OF THE SUPPLIER'S STANDARD CONDITIONS OF SALE.

Each user bears the full responsibility for making its own determination as to the suitability of Supplier's materials, products, services, recommendations or advice for its own particular purpose. Each user must identify and perform tests and analyses sufficient to assure it that its finished parts will be safe and suitable for use under end-use conditions. Because actual use of products by the user is beyond the control of Supplier, such use is within the exclusive responsibility of the user, and Supplier cannot be held responsible for any loss incurred through incorrect or faulty use of the products. Further, no statement contained herein concerning a possible or suggested use of any material, product, service or design is intended or should be construed to grant any license under any patent or other intellectual property right of Supplier or any of its subsidiaries or affiliated companies, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.